

Resinfam Product Selection Guide



Sales Dept
+9821-88885962

	Chemical Composition	Plasticizer	Solids Content (%)	pH Value	MFFT (°C)	Viscosity (cP)	Interior Paints	Exterior Paints	Gloss Paints	Wood Paints	Textured Coatings	Primers	Silicate Systems	Silicone Coatings	Crack Bridging Coatings	Flexible Coatings	Tile Adhesive	Plasters	Roof Coating	EIFS	Carpet Back Coatings	Woven Carpet Back Coating	Pigment Printing	Fabric Sizing	Glass Fiber Finishing	Non-woven Finishing	Wood Adhesive	Paper and Packaging Adhesive	Book Binding	Veneering	Laminating Adhesive	OPV	Dispersing Agent	Thickener			
Polyfam 101	Sodium Salt of a Polyacrylate	-	28 ± 2	9-11	NA	125-325																															
Polyfam 103	Acrylic Copolymer	-	28 ± 0.5	2-3	NA	<15																															
Polyfam 300	Vinyl Acetate	-	50 ± 1	3-5	+14	70,000-100,000															●	●				●	●	○									
Polyfam 301	Vinyl Acetate	-	50 ± 1	3-5	+14	100,000-140,000											○									●	●	●	○								
Polyfam 302	Vinyl Acetate	-	50 ± 1	3-5	+14	1,500 – 4,500																●															
Polyfam 320	Vinyl Acetate	+	50 ± 1	3-5	+9	60,000-90,000																●					○	●	●								
Polyfam 321	Vinyl Acetate	+	49 ± 1	3-5	+4	50,000-80,000																					○	●	●								
Polyfam 324	Vinyl Acetate	+	50 ± 1	4-5	+4	20,000-50,000																															
Polyfam 330	Vinyl Acetate	+	37 ± 1	4-5	+3	30,000-50,000																		●													
Polyfam 395	Vinyl Acetate	-	20 ± 1	5-7	<0	3,500-5,500	●				●																										
Polyfam 420	Vinyl Acetate/Acrylic/VeoVa	-	50 ± 1	4-5	<0	7,000-12,000	●	●			○																										
Polyfam 425	Vinyl Acetate/Acrylic	-	52 ± 1	4-5	<0	2,000-4,000	●	○			●					●		●																			
Polyfam 431	Vinyl Acetate/Acrylic	-	55 ± 1	4-5	<0	2,500-4,500	●	●																													
Polyfam 440	Vinyl Acetate/Acrylic	-	58 ± 1	4-5	<0	2,000-4,000	●	●			●																										
Polyfam 450	Vinyl Acetate/Acrylic	-	50 ± 1	4-5	+10	7,000-15,000																															
Polyfam 480	Vinyl Acetate/VeoVa	-	50 ± 1	6.5-7.5	+14	<1,000	●	●			○																										
Polyfam 5150	Vinyl Acetate/Acrylic	-	55 ± 1	4-6	+6	4,000-7,000	●	○			●						●	○																			
Polyfam MTB	Vinyl Acetate/Acrylic	-	40 ± 1	6-7	<0	30-60																		●													
Polyfam 706	Self Crosslinking Pure Acrylic	-	46 ± 1	2-3	+19	50-350																			○	●											
Polyfam 707	Styrene/Acrylic	-	50 ± 1	7-9	+16	2,000-5,000	●	●	○		○	●	●	●							●																
Polyfam 708	Styrene/Acrylic	-	50 ± 1	7-9	+21	2,000-5,000	●	●	●			●	●	●							●																
Polyfam 735	Styrene/Acrylic	-	50 ± 1	7.5-8.5	+15	2,000-5,000	●	●				●	●	●		○	●	●																			
Polyfam 748	Pure Acrylic	-	54 ± 1	7.5-9.5	<0	<200									●	●																					
Polyfam 765	Styrene/Acrylic	-	50 ± 1	7.5-8.5	0	2,000-5,000	●	●			●	●	●	●	●	●	○	●	○		●																
Polyfam 774	Pure Acrylic	-	50 ± 1	8.5-10.5	+17	50-150	●	●	●	●	○	●																									
Polyfam 777	Pure Acrylic	-	46 ± 1	8-9	+13	50-150	●	●	●	●	○	●																									
Polyfam 783	Self Crosslinking Styrene/Acrylic	-	40 ± 1	8-6	<0	<15																		●													
Polyfam PR578C	Styrene/Acrylic	-	46 ± 2	7.5-8.5	+12	1,000-1,400																														●	
Polyfam PR579C	Styrene/Acrylic	-	46 ± 2	7.5-8.5	+85	200-600																														●	

● Main application ○ Other applications